

# Marathon

Specification according to EN 1307

Type of manufacture	ISO 2424	Tufted 1/10 "						
Aspect	ISO 2424	Loop pile						
Dye method	Piece dyed continuous							
Width	cm	400	ft	13.1				
Primary backing	ISO 2424	Polypropylene woven + fleece						
Secondary backing	ISO 2424	Polypropylene woven - Sandwich Backing						
Pile fibre composition	ISO 2424	BCF Polyamide 6.6						
Total thickness	ISO 1765	mm	7.5	inch	0.3			
Effective pile thickness	ISO 1766	mm	5.0	inch	0.20			
Total mass	ISO 8543	g/m <sup>2</sup>	2250	oz/yd <sup>2</sup>	66.4			
Total pile mass	ISO 2424	g/m <sup>2</sup>	880	oz/yd <sup>2</sup>	26.0			
Effective pile mass	ISO 8543	g/m <sup>2</sup>	660	oz/yd <sup>2</sup>	19.5			
Pile density	ISO 8543	g/cm <sup>3</sup>	0.132	lb/in <sup>3</sup>	0.0048			
Number of tufts	ISO 1763	/dm <sup>2</sup>	1530	/yd <sup>2</sup>	127923			
Stroll test	ISO 6356	kV	≤ 2,0					
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307	33 Commercial - heavy use						
Luxury rating	EN 1307	LC 3						
Impact sound reduction ΔL <sub>w</sub>	ISO 10140	dB	25					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
			α <sub>s</sub>	0.01	0.03	0.12	0.29	0.58
Noise reduction	ISO 354	α <sub>w</sub>	0.20					
Thermal resistance	ISO 8302	m <sup>2</sup> .K/W	0.058					
Flammability	EN 13501-1	Bfl - s1 (glued tested)						
Prodis - GUT	www.pro-dis.info	C6AFED8B						

EN 14041  
 0493-CPR-0003

Manufactured by:  
 Tarkett BV  
 Parallelweg 14  
 NL - 5051 HG Goirle

Quality- and Environmental  
 Management System Certification  
 ISO 9001 & ISO 14001



Tarkett's flooring products are to be installed in full accordance with DESSO installation instructions and recognised trade standards. An effective, regular cleaning and maintenance programme is vital for retaining a high appearance level. Tarkett's flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit [professionals.tarkett.com](http://professionals.tarkett.com)

EN-20180921