



## MARLEY TILES (NSB) SUGGESTED SPECIFICATION\_



Supply and fix 1.25mm thick x 300mm x 300mm Marley Tiles NSB fully flexible vinyl tiles, laid in FloorworX No. 62 acrylic adhesive which has been spread using a trowel fitted with an A2 notched blade at a rate of between 5.5m<sup>2</sup> and 6.5m<sup>2</sup> per litre on a previously prepared Class 1 sub-floor in accordance with SANS 10070, using FloorworX Self Leveller when required, including all cutting and waste. The flooring must be rolled in both directions with an articulated 68kg three-sectional roller immediately after it has been laid into the adhesive. The newly laid floor must, after 72 hours, be stripped using FloorworX Stripper, scrubbed using a diluted solution of FloorworX Rinse and then sealed with 3 coats of FloorworX Silk Matt or Gloss Sealer.





