



Total Thickness		7.00mm	
Dimensions		Planks: 190mm x 1200mm	
Packaging		8 Planks Per Pack (1.8240m ²)	
Total Weight		6.20kg/m ²	
Colour Range		6 Selected Colours	
Tongue and Groove		Uniclic® Click System	
Use Classification	EN 13329	Class 21 Domestic - Moderate / Light Class 22 Domestic - Moderate / Medium Class 23 Domestic - Heavy Class 31 Commercial - Moderate Class 32 Commercial - General	
Abrasion Resistance	EN 13329 EN 13329	≥ 4000 Cycles AC4	Result: ≥ 4000 Cycles Result: AC4
Stain Resistance	EN 13329 Group 1, 2 Group 3	Class 5 Class 4	Result: Class 5 Result: Class 5
Moisture Resistance	EN 13329 - After 24 hour Immersion at 20°C.	18%	Result: 18%
Cigarette Resistance	EN 438-2, 30	Class 4	Result: Class 5
Light Fastness	EN 13329	Class 6	Result: > 6
Residual Indentation	EN 424	Foot: 0.1mm / 32kg Foot: 2mm / 100kg Foot: 3mm / 100kg	Result: No Change Result: No Change Result: No Change
Castor Wheel Test	EN 13329 25000 Cycles	Type W (EN 12529)	Result: No Change
Dimensional Stability	ISO 24339	≤ 0.10%	
Slip Resistance	EN 13893	DS	
Impact Sound Reduction	ISO 712-2	ΔLw = 18dB	Result: ΔLw = 19dB
Impact Resistance	EN 13329	IC2	Result: IC2
Scratch Resistance	EN 438-2, 25	Change: ≥ 3.0 N	Result: 5.0 N
Reaction to Fire	EN 14041	Cii - Si	
Thermal Resistance	ISO 8302	0.051m ² . K/W	
Underfloor Heating		Consult Special Installation Instructions.	
Formaldehyde Emissions	EN 717	E1 < 0.025ppm	
CE Conformity	EN 14041	0380-1161	
Sustainability of Forests		PEFC Label	
Environmental Product Declaration	ISO 14025	On Request	
General Aspects of Installed Floor	EN 13329 Lipping Opening between Joints General Flatness: Length General Flatness: Width	≤ 0.15mm ≤ 0.20mm Concave: ≤ 0.50% Convex: ≤ 1.00% Concave: ≤ 0.15% Convex: ≤ 0.20%	Result: ≤ 0.10mm Result: ≤ 0.10mm Result: Concave: ≤ 0.50% Result: Convex: ≤ 1.00% Result: Concave: ≤ 0.15% Result: Convex: ≤ 0.20%



It is advised to confirm stock availability on **0860 346 679**