



Total Thickness	ISO 24346	2.0mm
Wear Layer Thickness	ISO 24340	2.0mm
Dimensions	ISO 24341	Rolls: 2m x 23m
Packaging		46m ² Per Roll
Total Weight	ISO 23997	2.95kg/m ²
Colour Range		14 Selected Colours
Use Classification	ISO 10874	Class 34 Commercial - Very Heavy
	ISO 10874	Class 43 Industrial - Heavy
Reaction to Fire	EN ISO 13501-1 EN ISO 9239-1 EN ISO 11925-2	Bfl - S1 ≥ 8 kW/m ² Pass SR*
Castor Wheel Test	ISO 4918	Pass SR*
Residual Indentation	ISO 24343-1	Required Value: ≤ 0.10mm Best Measured Value: ≤ 0.02mm
Slip Resistance	DIN 51130	R9
Slip Resistance	EN 13893	Class DS μ ≥ 0.3
Fungi and Bacteria Resistance	EN ISO 846: Part C	Does not favour growth.
Chemical Resistance	ISO 26987	Good Resistance
Static Electrical Charge	EN 1815	< 2kV
Light Fastness	EN ISO 105-B02	≥ Level 7
Dimensional Stability	ISO 23999	≤ 0.40%
Seam Strength	EN 684	Average Value: ≥ 240 N/50mm Individual Values: ≥ 180 N/50mm
Ease of Decontamination	ISO 8690	Good
Electrical Insulation	VDE 0100, Part 600	R _i ≤ 5 x 10 ⁴ Ω
Electrical Resistance	ESD-approval SP method 2472 EN 1081 EN/IEC 61340-4-1 / 100V EN/IEC 61340-4-5	R ≤ 10 ⁹ Ω R ₁ 5 x 10 ⁴ ≤ R ≤ 10 ⁶ Ω R ₂ 5 x 10 ⁴ ≤ R ≤ 10 ⁶ Ω R 5 x 10 ⁴ ≤ R ≤ 10 ⁶ Ω ≤ 3.5 x 10 ⁷ Ω
Thermal Resistance	EN 12667	Approx. 0.01m ² k/W
Underfloor Heating		Suitable provided that the temperature of the surface of the sub-floor does not exceed 27°C.
Emissions	AgBB/DIBt	< 10μg/m ³ (TVOC after 28 Days)
Clean Room Test	ASTM F24 F51	Class A
CE Certification	EN 14041	Yes
Surface Treatment		iQ PUR
Flooring Type	ISO 10581	Permanently static conductive pressed homogeneous vinyl flooring
Binder Content	ISO 10581	Type 1



It is advised to confirm stock availability on **0860 346 679**

SR* = Standard Requirements