



Total Thickness		8.00mm	
Dimensions		Planks: 190mm x 1380mm	
Packaging		7 Planks Per Pack (1.8350m ²)	
Total Weight		7.575kg/m ²	
Colour Range		5 Selected Colours	
Tongue and Groove		Uniclic® Multifit System	
Use Classification	EN 13329	Class 21 Domestic - Moderate / Light Class 22 Domestic - Moderate / Medium Class 23 Domestic - Heavy Class 31 Commercial - Moderate Class 32* Commercial - General	
Abrasion Resistance	EN 13329 EN 13329	≥ 4000 Cycles ≥ 4000 Cycles	Class 32 (with overlay) AC4 (with overlay)
Stain Resistance	EN 13329 Group 1, 2 Group 3	Class 5 Class 4	Result: Class 5 Result: Class 5
Moisture Resistance	EN 13329 - After 24 hour Immersion at 20°C. Hydro-seal.	≤ 18% with water repel- lant coating all around.	Result: ≤ 12%
Cigarette Resistance	EN 438-2, 30	Class 4	Result: Class 5
Light Fastness (Grey Reference)	EN ISO 4892-2: 2006/A1:2009	Class ≥ 4	Result: Class 4
Residual Indentation	EN 424 (≤ 0.05mm)	Foot: 0.1mm / 32kg Foot: 2mm / 100kg Foot: 3mm / 100kg	Result: No Change Result: No Change Result: No Change
Castor Wheel Test	ISO 4918 (with underlay) 25000 Cycles	Type W (EN 12529)	Result: No Change
Dimensional Stability	EN 13329	≤ 0.9%	Result: ≤ 0.9%
Slip Resistance	EN 13893	Class DS μ ≥ 0.30	Result: Class DS μ ≥ 0.30
Impact Sound Reduction	ISO 712-2	ΔLw = 18dB	Result: ΔLw = 18dB * Dependent on the type of underlay used.
Impact Resistance	EN 13329	IC2	Result: IC2
Scratch Resistance	EN 438-2, 25	Change: ≥ 3.0 N	Result: 5.0 N
Reaction to Fire	EN 14041	Cfl - S1	
Electrical Behaviour	EN 14041	≤ 2.10kV	
Thermal Resistance	ISO 8302	0.055m ² . °K/W	
Underfloor Heating		Consult Special Installation Instructions.	
Formaldehyde Emissions	EN 717-1	E1 < 0.1	Result: E1 < 0.01ppm
CE Conformity	EN 14041	QL 0502	
Sustainability of Forests		PEFC Label	
General Aspects of Installed Floor	EN 13329 Lipping Opening between Joints General Flatness: Length General Flatness: Width	≤ 0.15mm ≤ 0.20mm Concave: ≤ 0.50% Convex: ≤ 1.00% Concave: ≤ 0.15% Convex: ≤ 0.20%	Result: ≤ 0.10mm Result: ≤ 0.10mm Result: Concave: ≤ 0.50% Result: Convex: ≤ 1.00% Result: Concave: ≤ 0.15% Result: Convex: ≤ 0.20%