

 **AREAS OF USE**

EDUCATION

SUGGESTED SPECIFICATION

Supply and fix 1.6mm / 2.0mm / 2.5mm thick x 300mm x 300mm Floorflex® semi-flexible vinyl tiles manufactured in accordance with SANS 581 and laid in FloorworX No. 62 acrylic adhesive which has been spread using a trowel fitted with an A2 notched blade at a rate of between 5.5m² and 6.5m² per litre on a previously prepared Class 1 sub-floor in accordance with SANS 10070, using a reliable Self-Leveller when required, including all cutting and waste. The flooring must be rolled in both directions with an articulated 68kg three-sectional roller immediately after it has been laid into the adhesive. The newly laid floor must, after 48 hours, be stripped using FloorworX Stripper, scrubbed using a diluted solution of FloorworX Rinse and then sealed with three coats of FloorworX Silk Matt or Gloss Sealer.



For more information please contact the **FloorworX TECHNICAL DEPARTMENT** by sending your query to technical@floorworx.co.za