



Total Thickness	EN-ISO 24346	3.4mm
Wear Layer Thickness	EN-ISO 24340	0.67mm
Dimensions		Rolls: 2m x 25m
Packaging		50m ² Per Roll
Total Weight	EN-ISO 23997	2.9kg/m ²
Colour Range		28 Selected Colour Colours 17 Selected Graphic Colours 32 Selected Material Colours 17 Selected Wood Colours
Use Classification	EN-ISO 10874 (EN 651)	Class 34 Commercial - Very Heavy
	EN-ISO 10874 (EN 651)	Class 42 Industrial - General
Reaction to Fire	EN ISO 13501-1	B _{fl} - s1 ⁰¹
Dimensional Stability	EN-ISO 23999	≤ 0.10% (Requirement: ≤ 0.40%)
Castor Wheel Test	EN 425 (ISO 4918)	Pass SR*
Residual Indentation	EN-ISO 24343-1	-0.08mm (Requirement: ≤ 0.20mm)
Furniture Leg Resistance	EN 424 (ISO 16581)	Compliant
Abrasion Resistance	EN 660-2	Group T
Slip Resistance	DIN 51130	R9
Slip Resistance	EN 13893	Class DS μ ≥ 0.3
Stain Resistance	EN-ISO 26987	Good
Static Electrical Charge	EN 1815	E ≤ 2kV, Antistatic
Light Fastness	EN ISO 105-B02 Method 3	Level 7 (Requirement: ≥ 6)
Underfloor Heating	EN 12524 (EN-ISO 10456)	Suitable provided that the temperature of the surface of the sub-floor does not exceed 27°C.
Sound Absorption	EN - ISO 354 EN - ISO 11654	α _w = ± 0.05 α _w = ± 0.05
Impact Sound Reduction	EN ISO 717-2	ΔL _w = 19dB
In-Room Impact Noise	NF S 31-074	L _{n,e,w} < 65dB, Class A
Surface Treatment		PUR
Emissions	EN-ISO 16000-9	< 20μg/m ³ (TVOC after 28 Days)
CE Conformity	EN 14041	0200825_DOP_306 - Conforms

⁰¹ Valid on every substrate: wood, non combustible A2_{fl}-s1 or A1_{fl}, or on free laying (with SARLIBASE TE underlayer)

⁰² Valid on non-combustible substrate: A2_{fl}-s1 or A1_{fl}

* TVOC : total volatile organic compounds_{fl}

SR* = Standard Requirements

Available in full rolls only.



It is advised to confirm stock availability on **0860 346 679**